

Product Description

PC 6020RT -F is a kind of polycarboxylate superplasticizer flake with higher water reducing rate and high collapse resistance.

In addition to the inherent characteristics of the powder water reducer, the biggest advantage is that it has very good collapse retention. It can be directly dissolved in water to prepare a liquid water reducing agent, and all indicators can reach the performance of a liquid polycarboxylic acid water reducing pumping agent, which makes the application process greatly convenient. For use in remote areas, simply stir and evenly dissolve it. The product has the characteristics of uniform particles, low water content, good solubility, high water reduction, and high collapse retention.

PC6020RT is based on EPEG polycarboxylate ether monomer.

PC 6020RT series have high degree slump retention rate, when use in concrete it need be used together with PC6010 series.

Specifications

Appearance	Buff or off-white flake
Moisture content	≤3%
Active Content	≥97%
Bulk density	500-650 g/l
pH value(20°C, 5% liquid)	5.0-7.0
Slump Time	≥90min
Water reducing rate	>15%

Application Range

After being configured as a liquid, this product is suitable for the use of liquid polycarboxylic acid water-reducing agents, and is suitable for pre-mixed and cast-in-situ concrete in various industrial and civil buildings. It is also used in high-strength, high-performance, high-durability, super-fluid, vibration-free, self-leveling, self-compacting and steel fiber special concrete; precast concrete, concrete for long-distance transportation, commercial concrete, etc.

It is especially suitable for construction sites in remote areas that are not suitable for building factories, and only simple pre-mixing equipment can meet the construction requirements.

Dosage

The recommended amount in various dry powder materials is 0.05-0.3% of the cementitious material. After dissolving, it can be used instead of liquid polycarboxylic acid water reducing agent, and after dissolving, it can be converted according to the actual solid content.

Such slump retention models should be used together with water reducing models, usually the ratio could be around,

Water reducing models: slump retention models =9:1/8:2/7:3

Key Properties

- The water reducing rate is more than 25% , can greatly improve the fluidity of the concrete with the same amount of water added.
 - In the spray drying process of traditional Polycarboxylate powder water reducing agent, due to the effect of high temperature, the polycarboxylic acid group will more or less cause certain damage. Thereby greatly reducing the performance of the product after the liquid is converted into a solid. PC-3050 is manufactured by a special process, so that the carboxylic acid group is not destroyed during the powder manufacturing process, so that the original liquid mother liquor is retained.
 - Good solubility and fast dissolution rate
- Especially the particles are uniform and the specific surface area is large. So it can dissolve quickly in the process of dissolving in water. And there is no obvious impurities after dissolution.

Packaging and Storage

- A. Standard Packing: In 25kg bags out HDPE bags inner with LDPE bags
- B. Big Bag or other special packages are possible on request.

Store it in a cool, dry place below 30° C and protected against humidity and pressing. Storage time should not exceed 12 months. And please use it up within 60days if the bags are open.

Safety Notes

The above data is in accordance with our knowledge, but don't absolve the clients carefully checking it all immediately on receipt. To avoid the different formulation and different raw materials, please do more testing before using it. We reserve the right to alter our product and without informing in advance.

Company Information

Shandong Charing Industry Co., Ltd.
Jinan City, Shandong Province, China
sdcharing@sdcharing.com
www.sdcharing.com